



Jiaxing Green Shield New Materials Co.,
 Ltd
 Add: No.365 West Qianjiang Road, Haining,
 Zhejiang, China

340gsm 10oz PVC Air Duct Fabric

Properties	Units	Test method	Average value
Base Thread Density	Denier	DIN53350	200D*500D
Base Fabric Density	Thread/inch	DIN53351	18*12
Finished Fabric Weight	Gram/m2	DIN53352	340
Base Fabric Weight	Gram/m2	DIN53352	50
Thickness - finished product	um	DIN53352	32
Break Strength Warp	N/5cm	GB/T1040	650
Break Strength Weft	N/5cm	GB/T1040	550
Tear Strength Warp	N/5cm	DIN 53363	150
Tear Strength Weft	N/5cm	DIN 53363	120
Adhension	N/5cm	DIN 53357	30
Temperature range	°C	DIN 53368	-30 ~ +70
Enviromental Standard	RoHs Reach	FR	M1