



Jiaxing Green Shield New Materials Co.,
Ltd
Add: No.365 West Qianjiang Road, Haining,
Zhejiang, China

510gsm 15oz PVC Laminated Fabric
Anti-UV, Color fastness,

Properties	Units	Test method	Average value
Base Thread Density	Denier	DIN53350	1300*1300D
Base Fabric Density	Thread/inch	DIN53351	9*9
Finished Fabric Weight	Gram/m2	DIN53352	510
Base Fabric Weight	Gram/m2	DIN53352	115
Thickness - finished product	um	DIN53352	40
Break Strength Warp	N/5cm	GB/T1040	1600
Break Strength Weft	N/5cm	GB/T1040	1400
Tear Strength Warp	N/5cm	DIN 53363	300
Tear Strength Weft	N/5cm	DIN 53363	280
Adhension	N/5cm	DIN 53357	120
Temperature range	°C	DIN 53368	-50 ~ +70
Flame Retardant	B2,Fire goes off within 3 seconds after remove fire resource,no fire drops		