



Jiaxing Green Shield New Materials Co.,  
 Ltd  
 Add: No.365 West Qianjiang Road, Haining,  
 Zhejiang, China

**590gsm 17oz PVC Fabric**  
**Anti-UV, Color fastness, anti-mold, fungus, Normal FR, 3P free**

Properties	Units	Test method	Average value
Base Thread Density	Denier	DIN53350	1000D*1000
Base Fabric Density	Thread/inch	DIN53351	9*9
Finished Fabric Weight	Gram/m2	DIN53352	600
Thickness - finished product	um	DIN53352	50
Break Strength Warp	N/5cm	GB/T1040	1300
Break Elongation	%	GB/T1040	25
Break Strength Weft	N/5cm	GB/T1040	1100
Break Elongation	%	GB/T1040	25
Tear Strength Warp	N/5cm	DIN 53363	300
Tear Strength Weft	N/5cm	DIN 53363	280
Adhension	N/5cm	DIN 53357	80
Temperature range	°C	DIN 53368	-30 ~ +70
Flame retardancy	Optional	Self-extinguishing	Optional