

Jiaxing Green Shield New Materials Co., Ltd
 Add: No.365 West Qianjiang Road, Haining, Zhejiang, China

Spec	Properties	Average value
500*1000 18*14	Weight	330g
	Break Strength Warp	2377.7n/5cm
	Break Strength Weft	2327.8n/5cm
	Tear Strength Warp	392.7n
	Tear Strength Weft	186.3n
	transmittance	
	permeability	

Spec	Properties	Average value
1300*1300 13*13	Weight	260±10
	Break Strength Warp	1864N/5cm
	Break Strength Weft	1845N/5cm
	Tear Strength Warp	363N
	Tear Strength Weft	350N
	transmittance	
	permeability	

Spec	Properties	Average value
1000D*1000D 9*9	Weight	240±10
	Break Strength Warp	1261N/5cm
	Break Strength Weft	1020N/5cm
	Tear Strength Warp	222N
	Tear Strength Weft	138N
	transmittance	
	permeability	

Spec	Properties	Average value
1000D*1000D 12*12	Weight	260±10
	Break Strength Warp	1100N/5cm
	Break Strength Weft	943N/5cm
	Tear Strength Warp	238N
	Tear Strength Weft	168N
	transmittance	
	permeability	

Spec	Properties	Average value
1000D*1000D 14*14	Weight	250±10
	Break Strength Warp	1650N/5cm
	Break Strength Weft	1691N/5cm
	Tear Strength Warp	260N
	Tear Strength Weft	299N
	transmittance	
	permeability	

Spec	Properties	Average value
4-pin checkered	Weight	500±20
	Break Strength Warp	531N/5cm
	Break Strength Weft	326N/5cm
	Tear Strength Warp	30N
	Tear Strength Weft	28N
	transmittance	
	permeability	

Spec	Properties	Average value
	Weight	300g
	Break Strength Warp	2059n/5cm

840*840 18*14	Break Strength Weft	1444n/5cm
	Tear Strength Warp	294. 2n
	Tear Strength Weft	115. 8n
	transmittance	40. 6%
	permeability	

Spec	Properties	Average value
1000*1000 9*9	Weight	450 ± 20g
	Break Strength Warp	2540N/5cm
	Break Strength Weft	2930N/5cm
	Tear Strength Warp	280N
	Tear Strength Weft	287N
	transmittance	
	permeability	

Spec	Properties	Average value
1000*1000 6*6	Weight	500G
	Break Strength Warp	2880N/5cm
	Break Strength Weft	2780N/5cm
	Tear Strength Warp	465N
	Tear Strength Weft	440N
	transmittance	
	permeability	

Spec	Properties	Average value
250D*250D 24*24	Weight	130 ± 10
	Break Strength Warp	503N/5cm
	Break Strength Weft	423N/5cm
	Tear Strength Warp	93N
	Tear Strength Weft	82N

	transmittance	
	permeability	

Spec	Properties	Average value
840D*8400D 20*12.5	Weight	320±10
	Break Strength Warp	2435N/5cm
	Break Strength Weft	1340N/5cm
	Tear Strength Warp	262N
	Tear Strength Weft	227N
	transmittance	
	permeability	

Spec	Properties	Average value
1000*1000 6*6	Weight	500G
	Break Strength Warp	3095N/5cm
	Break Strength Weft	2789N/5cm
	Tear Strength Warp	613N
	Tear Strength Weft	596N
	transmittance	
	permeability	

Spec	Properties	Average value
1000D*1000D 18*18	Weight	480
	Break Strength Warp	2365N/5cm
	Break Strength Weft	1850N/5cm
	Tear Strength Warp	272N
	Tear Strength Weft	228N

	transmittance	
	permeability	

Spec	Properties	Average value
1000D*1300D 10*13	Weight	200±10
	Break Strength Warp	1444N/5cm
	Break Strength Weft	740N/5cm
	Tear Strength Warp	339N
	Tear Strength Weft	149N
	transmittance	
	permeability	

Spec	Properties	Average value
1000*1000 4.5*4.5	Weight	170±10
	Break Strength Warp	582N/5cm
	Break Strength Weft	437N/5cm
	Tear Strength Warp	155N
	Tear Strength Weft	186N
	transmittance	
	permeability	

Spec	Properties	Average value
1000D*1000D 9*9	Weight	240±10
	Break Strength Warp	946N/5cm
	Break Strength Weft	917N/5cm
	Tear Strength Warp	242N
	Tear Strength Weft	110N
	transmittance	
	permeability	

Spec	Properties	Average value
500D*500D 18*18	Weight	210±10
	Break Strength Warp	1273N/5cm
	Break Strength Weft	1074N/5cm
	Tear Strength Warp	187N
	Tear Strength Weft	132N
	transmittance	
	permeability	

Spec	Properties	Average value
840D*500D 10*11	Weight	450±20
	Break Strength Warp	2687N/5cm
	Break Strength Weft	1983N/5cm
	Tear Strength Warp	144N
	Tear Strength Weft	287N
	transmittance	
	permeability	

Spec	Properties	Average value
1000D*1000D 9X9	Weight	240±10
	Break Strength Warp	1123N/5cm
	Break Strength Weft	1033N/5cm
	Tear Strength Warp	115N
	Tear Strength Weft	213N
	transmittance	
	permeability	

Spec	Properties	Average value
	Weight	120g

1000*1000 12*12	Break Strength Warp	1250n/5cm
	Break Strength Weft	1250n/5cm
	Tear Strength Warp	300n
	Tear Strength Weft	310n
	transmittance	37%
	permeability	2711mm/s

Spec	Properties	Average value
500D*500D 11*11	Weight	300±20
	Break Strength Warp	2070N/5cm
	Break Strength Weft	2045N/5cm
	Tear Strength Warp	116N
	Tear Strength Weft	102N
	transmittance	
	permeability	

Spec	Properties	Average value
1500D*1500D 14*14	Weight	175g
	Break Strength Warp	2577N/5cm
	Break Strength Weft	2080N/5cm
	Tear Strength Warp	356N
	Tear Strength Weft	406N
	transmittance	32.00%
	permeability	2900mm/s

Spec	Properties	Average value
	Weight	500±20g
	Break Strength Warp	2665N/5cm
	Break Strength Weft	2856N/5cm

1000*1000 9*9	Tear Strength Warp	243N
	Tear Strength Weft	253N
	transmittance	
	permeability	

Spec	Properties	Average value
840D*840D 10*11	Weight	500 ± 20g
	Break Strength Warp	3321N/5cm
	Break Strength Weft	3375N/5cm
	Tear Strength Warp	240N
	Tear Strength Weft	290N
	transmittance	19.00%
	permeability	1450mm/s

Spec	Properties	Average value
1000D*1000D 8*7	Weight	500 ± 20g
	Break Strength Warp	2495N/5cm
	Break Strength Weft	3025N/5cm
	Tear Strength Warp	355N
	Tear Strength Weft	420N
	transmittance	21.00%
	permeability	1978.7mm/s