

Materials Co., Ltd
Add: No. 365 West Qianjiang

Spec	Properties	Average value
1000*1000 9*9	Weight	250g
	Break Strength Warp	1100n/5cm
	Break Strength Weft	1100n/5cm
	Tear Strength Warp	230n
	Tear Strength Weft	220n
	transmittance	52%
	permeability	3199mm/s

Spec	Properties	Average value
1000*1000 9*13	Weight	260g
	Break Strength Warp	1100n/5cm
	Break Strength Weft	1300n/5cm
	Tear Strength Warp	300n
	Tear Strength Weft	280n
	transmittance	39.50%
	permeability	2945mm/s
	temperature	-30--70

Spec	Properties	Average value
500*1000 18*12	Weight	250g
	Break Strength Warp	900n/5cm
	Break Strength Weft	1050n/5cm
	Tear Strength Warp	170n
	Tear Strength Weft	180n
	transmittance	35.8%
	permeability	3979mm/s
	temperature	-30--70

Spec	Properties	Average value
840*500 10*11	Weight	400g
	Break Strength Warp	3100N/5cm
	Break Strength Weft	1800N/5cm
	Tear Strength Warp	190N
	Tear Strength Weft	110N
	transmittance	18.30%
	permeability	1403mm/s

Spec	Properties	Average value
1212	Weight	150g
	Break Strength Warp	1250N/5cm
	Break Strength Weft	1250N/5cm
	Tear Strength Warp	450N
	Tear Strength Weft	427N
	transmittance	
	permeability	

Spec	Properties	Average value
1000*1000 12*12	Weight	260g
	Break Strength Warp	1250n/5cm
	Break Strength Weft	1250n/5cm
	Tear Strength Warp	300n
	Tear Strength Weft	310n
	transmittance	44%
	permeability	2711mm/s

Spec	Properties	Average value
1000*1000 6*6	Weight	220g
	Break Strength Warp	850n/5cm
	Break Strength Weft	820n/5cm
	Tear Strength Warp	180n
	Tear Strength Weft	189n
	transmittance	59%
	permeability	6983mm/s

Spec	Properties	Average value
1000*1000 18*9	Weight	270g
	Break Strength Warp	2200n/5cm
	Break Strength Weft	1100n/5cm
	Tear Strength Warp	350n
	Tear Strength Weft	230n
	transmittance	33.50%
	permeability	2260mm/s

Spec	Properties	Average value
500*500 18*20	Weight	220g
	Break Strength Warp	1100n/5cm
	Break Strength Weft	1100n/5cm
	Tear Strength Warp	230n
	Tear Strength Weft	220n
	transmittance	31.20%
	permeability	2080mm/s

Spec	Properties	Average value
1000*1000 12*12	Weight	300g
	Break Strength Warp	1852n/5cm
	Break Strength Weft	1497n/5cm
	Tear Strength Warp	350n
	Tear Strength Weft	176n
	transmittance	
	permeability	